


MAGNET

* ANISOTROPIC RUBBER MAGNET

MODEL \ DIM.	A / ± 0.20 - 0.20	B / ± 0.20 - 0.00	C / ± 0.2
ME - 20 - 9 × 4	19.50	9.00	4.00
ME - 25 - 13 × 4	24.50	13.00	4.00
ME - 30 - 21 × 4	29.50	21.00	4.00
ME - 32 - 21 × 4	31.50	21.00	4.00
ME - 40 - 22 × 4	39.50	22.00	4.00
ME - 50 - 32 × 4	49.50	32.00	4.00
ME - 63 - 42 × 4	62.50	42.00	4.00
ME - 80 - 58 × 4	79.50	58.00	4.00
ME - 100 - 78 × 4	99.50	78.00	4.00
ME - 125 - 78 × 4	124.50	78.00	4.00
ME - 125 - 108 × 4	124.50	108.00	4.00
ME - 150 - 125 × 4	149.50	125.00	4.00

MODEL \ DIM.	A / ± 0.20 - 0.20	B / ± 0.20 - 0.00	C / ± 0.2
ME - 20 - 9 × 5	19.50	9.00	5.00
ME - 25 - 13 × 5	24.50	13.00	5.00
ME - 30 - 21 × 5	29.50	21.00	5.00
ME - 32 - 21 × 5	31.50	21.00	5.00
ME - 40 - 22 × 5	39.50	22.00	5.00
ME - 50 - 32 × 5	49.50	32.00	5.00
ME - 63 - 42 × 5	62.50	42.00	5.00
ME - 80 - 58 × 5	79.50	58.00	5.00
ME - 100 - 78 × 5	99.50	78.00	5.00
ME - 125 - 78 × 5	124.50	78.00	5.00
ME - 125 - 108 × 5	124.50	108.00	5.00
ME - 125 - 108 × 5	149.50	125.00	5.00



CHARACTERISTIC :

A. Magnetek properties:

Residual flux density (Br): 2300 - 2500 Gs
 Coercive force (Hcb): 3000 - 3800 Oe
 (Hcj): 2000 - 2300 Oe
 (BH)max: 1.3 - 1.5 MGOe


B. Physical properties:

Tensile strength: 20 ~ 60 kgf/cm²
 Elongation: >20 %
 Hardness (Shore D): 30 ~ 50
 Density: 3.3 - 3.9 g/cm³

* ANISOROPIC PLASTIC MAGNET

MODEL \ DIM.	A / ± 0.20 - 0.20	B / ± 0.20 - 0.00	C / ± 0.2
GME - 16 - 8 × 4	15.50	8.00	4.00
GME - 20 - 9 × 4	19.50	9.00	4.00
GME - 25 - 13 × 4	24.50	13.00	4.00
GME - 30 - 21 × 4	29.50	21.00	4.00
GME - 32 - 21 × 4	31.50	21.00	4.00
GME - 40 - 22 × 4	39.50	22.00	4.00
GME - 50 - 32 × 4	49.50	32.00	4.00
GME - 63 - 42 × 4	62.50	42.00	4.00
GME - 80 - 58 × 4	79.50	58.00	4.00
GME - 100 - 78 × 4	99.50	78.00	4.00

MODEL \ DIM.	A / ± 0.20 - 0.20	B / ± 0.20 - 0.00	C / ± 0.2
GME - 16 - 8 × 5	15.50	8.00	5.00
GME - 20 - 9 × 5	19.50	9.00	5.00
GME - 25 - 13 × 5	24.50	13.00	5.00
GME - 30 - 21 × 5	29.50	21.00	5.00
GME - 32 - 21 × 5	31.50	21.00	5.00
GME - 40 - 22 × 5	39.50	22.00	5.00
GME - 50 - 32 × 5	49.50	32.00	5.00
GME - 63 - 42 × 5	62.50	42.00	5.00
GME - 80 - 58 × 5	79.50	58.00	5.00
GME - 100 - 78 × 5	99.50	78.00	5.00



CHARACTERISTIC :

A. Magnetek properties:

Residual flux density (Br): 2.5 ~ 3.3 KGs
 Coercive force (Hcb): 2.1~ 2.5 KOe
 (Hcj): 2.6 ~ 3.4 KOe
 (BH)max: 1.5 ~ 2.5 MGOe

B. Physical properties:

Tensile strength: 90 kgf/cm²
 Lengthen: <7 %
 Hardness (Shore D):130 ~ 150
 Density: 3.0 g/cm³